

VL0005

Description

Characteristics	<ul style="list-style-type: none"> ▪ Excellent Heat Seal Properties at lower Temperature ▪ Excellent Hot Tack Strength 	<ul style="list-style-type: none"> ▪ Excellent Sealability of Powder's goods ▪ High Clarity
Applications	<ul style="list-style-type: none"> ▪ Multi-layer Films (Sealant Layer) ▪ High Strength Industrial Packaging Film ▪ Modifier of Impact Properties 	
Processing Recommendation	Processing Temperature ~ 250°C	
Specification data	Complies with FDA 21 CFR 177.1520	

Physical Properties

Resin Properties	Unit	Test Method	VL0005
Density	g/cm ³	ASTM D1505	0.900
Melt Index (190°C, 2.16kg)	g/10min	ASTM D1238	5.0
Vicat Softening Temperature	°C	ASTM D1525	82
Melting Temperature	°C	ASTM D3418	95
Additives	-	-	AO
Film Properties	Unit	Test Method	VL0005
Tensile Strength at Break (MD/TD)	kg/cm ²	ASTM D882	440/330
Elongation at Break (MD/TD)	%	ASTM D882	380/600
Dart Impact Strength (B)	gf	ASTM D1709	350
Haze	%	ASTM D1003	0.5
Gloss (45°)	-	ASTM D2457	110
Seal Initiation Temperature (HGT, 2.8KG, 0.5sec)	°C	Daelim	92

1. Film Processing Condition : Φ50mm Cast Film Extruder, 250°C, Film thickness 0.022mm
2. Additives : AO (Antioxidant)
3. These are typical properties only and are not to be construed as specifications.

*NOTICE: Prior to use for any commercial purpose, the customer is fully responsible for determining its suitability for intended application and for ensuring its disposal practices are in compliance with applicable laws and other governmental enactments. DAELIM assumes no obligation or liability in this regard. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.